

Test Report

Applicant: ACEGREEN ECO-MATERIAL TECHNOLOGY CO.,
LTD.
No. 50, Ln. 20, Sec. 1, Nantong Rd.,
Ershui Township, Changhua County 530,
Taiwan, R.O.C.

Number : TWNC00938154

Date Issued : Dec 03, 2020

Sample Description:

One (1) Piece of Submitted Sample Said To Be :

Item Name : Antibacterial Melt-Blown Nonwoven
Item No. : ACE-M-001/GCE0175L
Color : Natural
Quantity : 1 Piece
Manufacturer : ACEGREEN ECO-MATERIAL TECHNOLOGY CO., LTD
Buyer : ACEGREEN ECO-MATERIAL TECHNOLOGY CO., LTD
Country of Origin : Taiwan
Date Sample Received : Nov 24, 2020
Date Test Started : Nov 24, 2020

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited

Carol Peng
General Manager



Signed by:



Thomas Chou
Manager



Test Conducted :

1. Antibacterial Activity Test

As per AATCC TM100-2019.

Test Organism : *Staphylococcus aureus* (ATCC 6538P)
 Sterilization Of Sample Before Test : No Sterilization
 Neutralizing Solution : Dey Engley Broth
 Concentration Of Surfactant : 0.05% Triton X-100
 Contact Time : 24 Hours
 Incubation Temperature : 37±2°C
 Incubation Period : 24-48 Hours
 Agar Medium : Nutrient Agar
 Swatches Weight : 1.0±0.1 g

Tested Specimen : Submitted Sample (Swatches with 3.8 X 3.8±0.1 cm)

Result :

<u>Name Of Test Bacteria</u> <u>(Strain Number)</u>	<i>Staphylococcus aureus</i> (ATCC 6538P)
The number of bacteria recovered from the inoculated viability control fabric swatches immediately after inoculation ("0" contact time) (D)	1.47 x 10 ⁵ CFU/Sample
The number of bacteria recovered from the inoculated viability control fabric swatches incubated over 24 hours contact period (B)	2.80 x 10 ⁶ CFU/Sample
The number of bacteria recovered from the inoculated tested sample swatches immediately after inoculation ("0" contact time) (C)	1.36 x 10 ⁵ CFU/Sample
The number of bacteria recovered from the inoculated tested sample swatches incubated over 24 hours contact period (A)	5.38 x 10 ³ CFU/Sample
Growth value (F)	1.28
Percent reduction of Bacteria (R)	96.04%

Calculation of percent reduction of Bacteria:

$$R = (C-A)/C \times 100\%$$

$$F = \text{Log B} - \text{Log D}$$

Remarks : CFU = Colony forming unit

Viability control fabric = Cotton standard adjacent fabric(cotton No.3) specified in JIS L0803





End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-tn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.

